

# PLEXTURE<sup>®</sup>

## LOW PROFILE TEXTURED COATING

# T110

### DESCRIPTION

- A two component interior, water-based, high solids, pure acrylic coating designed to deliver excellent performance results at an economical price. Applied directly to most common construction substrates.
- Class "A" non-combustible, non-toxic, low VOC.
- Use instead of traditional paint and texture, or as a cost savings to vinyl wall covering.

### ADVANTAGES

- Durable, abuse resistant, easily cleaned, low maintenance.
- Life cycle 8 -10 years with active use.

### 5-YEAR WRITTEN WARRANTY PERFORMANCE

Against peeling, delaminating, cracking, and chalking.

### 5-YEAR WRITTEN MOLD/MILDEW WARRANTY

- Against mold and mildew growing on the surface of Plecture.
- Full details available by contacting Triarch.
- ASTM D3273-00 Resistance to Mold – extended testing = 10 (no growth)

### SCRUBBABLE

- Not damaged by water.

- Most marks and scuffs removed after 7 – 10 days of curing, using a stiff scrub brush with liquid soap and water.

### DESIGN OPTIONS

Available in a variety of patterns and almost unlimited integral colors, both in monochromatic and multi-color finishes. Call TRIARCH for samples.

### DELIVERY TIME

Quick ship, smaller shipments leave the centrally located factory within 48 hours after a placed order. Custom samples and larger orders may take a bit longer (up to 5-10 days).

### FACTORY TRAINED APPLICATORS\*

- Over 600 factory trained applicators available nationally.
- National training program helps to ensure quality control and minimize installation time.

### COST

- Most projects with standard finishes install between \$.55 - \$.75 per square foot. Premium finishes are around \$0.90 - \$1.20
- Actual job conditions, volume, wall elevations, and local labor may affect installed prices.

### PRODUCT DATA

### SPECIFICATIONS

- Water based acrylic
- Integral and Colorfast Pigments
- ASTM E-84-95, Flame spread = 15
- Smoke Contribution = 0
- ASTM E-96B, English Wet Perms = 21.93
- VOC level per ISO 11890-2 less than 20 g/L
- ASTM D2486 Scrub 4300 cycles Landscape 3500 cycles Sierra
- ASTM D3273-00 Mold = 10 (extended test: no growth)
- Dry film thickness of a random 4 – 10 mils depending upon pattern

### SHIPPING AND STORAGE

- Shipped in 5 gallon plastic pails
- Protect from freezing
- Protect from heat over 100°F.
- Stack to maximum of three (3) pails high.
- One (1) year shelf life.

### APPLICATION

Applied with traditional painter's tools – airless and/or texture sprayer. Sequence depends upon selected finish. Two components make the Plecture System: Texture Coat and FineCoat 2. Installation video available upon request.

\* TRIARCH DOES NOT WARRANT, GUARANTEE, OR ASSUME LIABILITY FOR THE WORKMANSHIP OF THE APPLICATOR

Triarch  
P.O. Box 1014  
One Energy Way  
West Warwick, RI 02893  
800-537-6111  
www.triarchinc.com

This information conforms to the standard detail recommendations and specifications for the installation of Triarch products as of the date of publication of this document and is presented in good faith. Triarch assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Triarch. Triarch expressly disclaims all implied warranties, including without limitation, implied warranties of merchantability and fitness for a particular purpose.



A Division of Dryvit Systems, Inc.