

SAND STORM[®]

HIGH PERFORMANCE SEAMLESS INTERIOR COATING

T112

DESCRIPTION

- An interior or exterior, high solids, one part water based acrylic coating using natural aggregates to provide a subtle pixelated wall finish.
- Designed to deliver high performance results at a moderate price.
- Applies directly to most clean, sound, unpainted common substrates. Class "A" non-combustible, non-toxic, very low VOC.

ADVANTAGES

- Very durable.
- Improves the strength of drywall and provides a highly scratch resistant surface.

5-YEAR WRITTEN PERFORMANCE WARRANTY

Against peeling, delaminating, cracking, and chalking.

5-YEAR WRITTEN SURFACE MOLD/MILDEW WARRANTY

- High perm rate to achieve breathability.
- Engineered formulation which virtually eliminates food sources for organisms combined with a long term mildewcide that provides unequalled performance.

SCRUBBABLE

- Not damaged by water.
- Most marks and scuffs removed after 7 – 10 days of curing, using a stiff scrub brush with liquid soap and water.

DESIGN OPTIONS

- Ten (10) standard color combinations along with textural effect/patterns. Some custom color capabilities and almost unlimited integral colors.
- Call TRIARCH for samples or a design binder.

DELIVERY TIME

Standard colors available within 1 week.

FACTORY TRAINED APPLICATORS *

- Factory trained applicators available nationally and internationally.
- We offer training programs to help insure quality control and minimize installation time.

COST

- Most projects install between \$4.00 - \$5.00 per square foot.
- Job conditions, wall elevations, local labor cost, and quantity purchased may affect installed prices.

PRODUCT DATA

SPECIFICATIONS

- Water based acrylic
- Integral & Colorfast Pigments
- ASTM D 4213-83 Scrub Cycles: passes
- ASTM E-84, Flame spread < 25, = Class 1
- ASTM D 3273 Mildew resistance: passes

- ASTM G154 Accelerated weathering: after 5000 hours no deleterious effects
- ASTM D 2247 Moisture Resistance: after 42 days: no deleterious effects
- ASTM E-96, Vapor Permeable, Perms = 45
- Final dry film thickness of 1/16-1/8 inch

SHIPPING AND STORAGE

- Shipped in 5 gallon plastic pails
- Protect from freezing
- Protect from heat over 100°F.
- Stack to maximum of three (3) pails high
- Two (2) year shelf life

APPLICATION

Color-coordinated primer shall be applied to all substrates a minimum of four hours prior to application of Sand Storm finish. Sand Storm finish should be applied in two coats, both trowel applied. A trowel with rounded edges, such as a pool trowel or Venetian Plaster trowel, should be used to eliminate trowel marks. Alternatively, a plastic knock down blade may be used to smooth the wet material on the wall. If spray application is desired to accelerate the application, the use of a plastic knock down blade, while the material is wet on the wall, will be required to achieve the desired smooth finish. Spray left to right, then double back with an up and down motion. See website for more details.

***TRIARCH DOES NOT WARRANT, GUARANTEE, OR ASSUME LIABILITY FOR THE WORKMANSHIP OF THE APPLICATOR**

Triarch
P.O. Box 1014
One Energy Way
West Warwick, RI 02893
800-537-6111
www.triarchinc.com
Printed in USA 2/09/07
©Triarch 2007

This information conforms to the standard detail recommendations and specifications for the installation of Triarch products as of the date of publication of this document and is presented in good faith. Triarch assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To ensure that you are using the latest, most complete information, contact Triarch. Triarch expressly disclaims all implied warranties, including without limitation, implied warranties of merchantability and fitness for a particular purpose.

TRIARCH
FINE ARCHITECTURAL FINISHES

A Division of Dryvit Systems, Inc.

