

T652

Spatula Stuhhi Mixing Instructions



Tools Needed: Water, small mixing spatula's, Box blade mixer, and a heavy duty variable speed drill.



Before tinting Spatula Stuhhi the additivo (pigment) must be stirred to ensure that there is no settling of the additivo.



Upon opening the Spatula Stuhhi base and removing the plastic insert there may be liquid that has risen to the top of the base. **DO NOT MIX THIS INTO THE PRODUCT.** Dump out any liquid before adding additivo.



Using a box blade mixer and drill, premix the base so that it has a more liquid consistency rather than a paste. Water is not necessary to achieve this. The more you mix Spatula Stuhhi the more liquid the product becomes. This will make incorporating the additivo easier.

COPYRIGHT PROTECTED

TRIARCH

www.triarchinc.com

401-822-4100 TEL 800-537-6111 Toll Free


401-822-2984 FAX

Spatula Stuhhi

Mixing Instructions



After premixing the base and stirring the additive. **Add additive to the base while mixing.** Using a variable speed drill create a vortex into which the additive is added. Do not add additive faster than the vortex can handle. This will ensure that the additive is incorporated into the base and not stuck on the side of the pail.



Once all the additive is added to the pail, (scrape out additive container), mix for approximately 2 minutes to ensure the additive is incorporating.



Using a small mixing spatula or paint stirrer. Scrape the sides of the pail to make sure all un-tinted base material is free from the side of the pail.



Mix for an additional 3 minutes to ensure the additive is fully incorporated into the base. The product will be of a uniform color with no white streaks of un-tinted base or streaks of un-mixed additive. Mix for additional time if necessary.

COPYRIGHT PROTECTED

TRIARCH

www.triarchinc.com

401-822-4100 TEL 800-537-6111 Toll Free

401-822-2984 FAX

T652

Spatula Stuhhi Mixing Instructions



Do Not apply Spatula Stuhhi for 24 hours after mixing. This will allow the product to solidify into the proper mixing consistency.

COPYRIGHT PROTECTED

TRIARCH

www.triarchinc.com

401-822-4100 TEL 800-537-6111 Toll Free

401-822-2984 FAX

Page 3